

Technical Data

INTELLATHANE® 7200

DESCRIPTION

Intellathane® 7200 is a 100% solids pure polyurea spray elastomer with exceptional physical properties. Its instantaneous reactivity and one-to-one ratio makes Intellathane® 7200 an excellent choice for high performance applications.

PROPOSED USES

Intellathane® 7200 is designed for use in harsh environments where high temperature, chemical, and/or abrasion resistance is needed. This advanced UV formulation is comparable to black aliphatic formulations.

TYPICAL PROPERTIES

Property	Test Method	<u>"A"</u>	<u>"B"</u>
Color	N/A	Off-white	Amber/ Black
Specific Gravity	ASTM D-1638	1.12	1.08
Viscosity	Brookfield LVF	900 cps +100	1000 cps + 100
Mixing Ratio	By Volume	50	50
Pounds Per Gallon	From Spec. Gravity	10.3	8.3



www.accellapolyurethane.com
2500 Adie Road, Maryland Heights, MO
Phone (314) 872-8700 | Fax (314) 872-9750

Technical Data

PHYSICAL PROPERTIES

DENSITY (PCF)	(ASTM D-1622)	70
SHORE A HARDNESS	(ASTM D-2240)	90 - 95
SHORE D HARDNESS	(ASTM D-2240)	60
TENSILE STRENGTH	(ASTM D-2370)	2900 psi minimum
ELONGATION	(ASTM D-2370)	225% minimum
TEAR STRENGTH	(ASTM D-1004)	550 ppi minimum
TABER ABRASION (H-18 WHEEL, 1000 CYCLES)		0.013% weight loss

Call **Accella Polyurethane Systems** for technical questions. 770-607-0755.

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. ACCELLA POLYURETHANE SYSTEMS WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES ACCELLA POLYURETHANE SYSTEMS, EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE ACCELLA POLYURETHANE SYSTEMS OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.



www.accellapolyurethane.com
2500 Adie Road, Maryland Heights, MO
Phone (314) 872-8700 | Fax (314) 872-9750